

QUALITY: Bleached Kraft (SG)				
GSM		32	40	60
Parameters	Unit			
Brightness	% PV	78	78	78
Bulk	cc/gm	1.1	1.1	1.1
Tensile Strength	kg	2.4	3.3	5.1
Breaking Length (MD)	meter	5000	5500	5700
Breaking Length (CD)	meter	2500	3100	3200
Tear Factor (MD)	-	40	47	80
Tear Factor (CD)	-	60	70	110
Bursting Strength	kg/cm ²	0.96	1.4	2.16
Burst Factor	-	24	28	28
Smoothness (Gurley) T/S	sec/100mL	1000	1000	1000
Smoothness (Gurley) B/S	sec/100mL	700	700	700
Porosity (Gurley)	sec/100mL	40	60	100
Cobb-60	g/m ²	22	22	22
Moisture	%	4 ± 0.5	4 ± 0.5	4 ± 0.5
pH		7 ± 0.2	7 ± 0.2	7 ± 0.2