

QUALITY: C1S (H.S.)			
GSM		50	70
Parameters	Unit		
Brightness	% PV	84	84
Bulk	cc/gm	1.0	1.0
Tensile Strength	kg	3.2	3.8
Breaking Length (MD)	meter	4300	3700
Breaking Length (CD)	meter	2200	2000
Tear Factor (MD)	-	50	70
Tear Factor (CD)	-	65	80
Bursting Strength	kg/cm ²	1.0	1.3
Burst Factor	-	22	24
Smoothness (Gurley) T/S	sec/100mL	1350	1900
Smoothness (Gurley) T/B	sec/100mL	800	800
Porosity (Gurley)	sec/100mL	1000	1500
Cobb-60	g/m ²	22	24
Moisture	%	5.5	5.5
pH		7.5	7.5
Gloss	%	65	70
SOA	sec	120	200