

QUALITY: C1S (STD.)

GSM		60	70	80	90
Parameters	Unit				
Brightness	% PV	85	85	85	85
Bulk	cc/gm	0.9	0.9	0.9	0.9
Tensile Strength	kg	3.0	2.8	3.9	4.4
Breaking Length (MD)	meter	3300	2700	3200	3200
Breaking Length (CD)	meter	2000	1700	1900	1900
Tear Factor (MD)	-	63	55	80	85
Tear Factor (CD)	-	73	75	85	90
Bursting Strength	kg/cm ²	1.32	1.26	1.28	1.35
Burst Factor	-	22	18	16	15
Smoothness (Gurley) T/S	sec/100mL	2000	2000	2100	2200
Smoothness (Gurley) B/S	sec/100mL	800	800	800	800
Porosity (Gurley)	sec/100mL	850	950	1100	1200
Cobb-60	g/m ²	24	26	26	26
Moisture	%	5.5	5.5	5.5	5.5
pH		7.5	7.5	7.5	7.5
Gloss		65	65	70	70
SOA		70	75	85	90