

QUALITY: Eco				
GSM		36	40	60
Parameters	Unit			
Brightness	% PV	64	64	64
Bulk	cc/gm	1.30	1.30	1.30
Tensile Strength	kg	1.3	1.9	3.0
Breaking Length (MD)	meter	2800	3200	3400
Breaking Length (CD)	meter	1700	2000	2000
Tear Factor (MD)	-	32	35	55
Tear Factor (CD)	-	40	48	65
Bursting Strength	kg/cm ²	0.5	0.6	1.1
Burst Factor	-	15	16	18
Smoothness (Gurley) T/S	sec/100mL	200	200	200
Porosity (Gurley)	sec/100mL	18	22	40
Cobb-60	g/m ²	22	22	22
Moisture	%	4 ± 0.5	4 ± 0.5	4 ± 0.5
pH		7 ± 0.2	7 ± 0.2	7 ± 0.2