

QUALITY: Premium SG				
GSM		36	40	60
Parameters	Unit			
Brightness	% PV	80	80	80
Bulk	cc/gm	1.1	1.1	1.1
Tensile Strength	kg	1.9	2.7	4.5
Breaking Length (MD)	meter	4000	4500	4800
Breaking Length (CD)	meter	2200	2600	2800
Tear Factor (MD)	-	35	42	60
Tear Factor (CD)	-	45	55	75
Bursting Strength	kg/cm ²	0.5	0.9	1.3
Burst Factor	-	18	22	22
Smoothness (Gurley) T/S	sec/100mL	1000	1000	1000
Smoothness (Gurley) B/S	sec/100mL	800	800	800
Porosity (Gurley)	sec/100mL	30	40	60
Cobb-60	g/m ²	22	22	22
Moisture	%	4 ± 0.5	4 ± 0.5	4 ± 0.5
pH		7 ± 0.2	7 ± 0.2	7 ± 0.2