

QUALITY: Super Deluxe				
GSM		36	40	60
Parameters	Unit			
Brightness	% PV	75	75	75
Bulk	cc/gm	1.30	1.30	1.30
Tensile Strength	kg	1.7	2.2	3.6
Breaking Length (MD)	meter	3200	3700	4000
Breaking Length (CD)	meter	1600	1900	2000
Tear Factor (MD)	-	34	40	55
Tear Factor (CD)	-	44	55	70
Bursting Strength	kg/cm ²	0.6	0.85	1.3
Burst Factor	-	18	20	22
Smoothness (Gurley) T/S	sec/100mL	220	220	220
Porosity (Gurley)	sec/100mL	18	24	45
Cobb-60	g/m ²	22	22	22
Moisture	%	4 ± 0.5	4 ± 0.5	4 ± 0.5
pH		7 ± 0.2	7 ± 0.2	7 ± 0.2