

QUALITY: Pulpure		
GSM		40
Parameters	Unit	
Brightness	% PV	90
Bulk	cc/gm	1.1
Tensile Strength	kg	4.1
Breaking Length (MD)	meter	6800
Breaking Length (CD)	meter	4200
Tear Factor (MD)	-	54
Tear Factor (CD)	-	75
Bursting Strength	kg/cm ²	1.4
Burst Factor	-	36
Smoothness (Gurley) T/S	sec/100mL	1150
Smoothness (Gurley) T/B	sec/100mL	1080
Porosity (Gurley)	sec/100mL	18
Cobb-60	g/m ²	22
Moisture	%	4
pH		7
Opacity	% PV	68
Gloss	% PV	37